

Crisper® K2411

Property	Unit	Product type		Test Method	
		Mat			
		K2411			
Thickness	μm	50	75	JIS C-2318	
Gravity	g/cm^3	1.1	1.1	JIS K-7112	
Total Luminous Transmittance	%	11.0	8.1	JIS K-7105	
Tensile Strength	MD	MPa	128	125	JIS C-2318
	TD		145	149	
Tensile Elongation	MD	%	105	107	JIS C-2318
	TD		55	53	
Thermal Shrinkage (150°C × 30min)	MD	%	1.3	1.1	JIS C-2318
	TD		0.6	0.4	
Ink Adhesion (UV Ink)	-	○	○	TOYOBO method	
Surface Resistivity	$\log\Omega$	10.8	10.5	JIS K-6911	

Remark : Above data is typical value, not guaranteed.

TOYOBO CO., LTD.
International Industrial Films Sales Department

Head office:
2-8, Dojima Hama 2-Chome, Kita-Ku, Osaka, 530-8230 JAPAN
TEL.+81-6-6348-4123
FAX.+81-6-6348-4160

Tokyo Branch:
Sumitomo Corporation Kyobashi Building, 17-10, Kyobashi 1-chome,
Chuo-ku, Tokyo 104-8345, Japan
TEL.+81-3-6887-8898
FAX.+81-3-6887-8894